

## ASLAN WB 995

### The white opaque whiteboard film

High quality whiteboard film, ideal for conference rooms, schools and kindergardens. Also as info board, such as in hotels or clinical practices.

The whiteboard film ASLAN WB 995 has a long durability and is dry-wipeable. Resistant to dirt and water, easy to clean.

ASLAN recommends the usage of whiteboardmarkers.

## Technical data

### Construction

<b>face-film:</b>	polyester / PVC	
<b>thickness:</b>	~ 130 µm	
<b>adhesive:</b>	acrylic pressure adhesive	square quantity: ~ 22 g/m <sup>2</sup>
<b>release liner:</b>	silicon paper	square weight: ~ 140 g/ m <sup>2</sup>

### Characteristics

<b>dimensional stability:</b>	applicated onto aluminium after 48 hours at 70 °C (25 x 25 cm)	max. -0,45%
<b>adhesive strength (ASTMD-903):</b>	immediately: after 1 week:	min. 1,0 N/cm min. 5 N/cm
<b>temperature:</b>	min. application temperature: ab 15 °C	service temperature range: -30°C bis + 80°C

**chemical resistance:** resistant to most petroleum based oils, greases and aliphatic solvents. Resistant to mild acids, alkalies, and salts.

**combustibility:** stuck on aluminium, the film is self-extinguishing.

## ASLAN WB 995

## The white opaque whiteboard film

### Processing

**printing:**

Not printable.

**application:**

Should only be applicated dry, as due to the two-layers drying time could be prolonged.

**storage properties:**

Before application the foils can be stored for minimum 3 years from date of production. The films must be stored at room temperature (15 – 25 °C) and be protected from direct sunlight, excessive heat, high atmospheric humidity and dampness. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either on end or on purpose design `hanging` racks.

Date: 04/2006

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.  
The quality of our products is regularly examined, upgraded and developed. ASLAN, Schwarz GmbH & Co. KG reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

**ASLAN, Schwarz GmbH & Co. KG**

Postf./POB 5165 • D-51486 Overath • Oberauel 2 • D-51491 Overath • Germany  
Tel.: +49 (0)2204/708-80 • Fax: +49 (0)2204/708-50 • UST-ID-Nr. DE121964163  
E-Mail: Info@ASLAN-Schwarz.com • Internet: www.ASLAN-Schwarz.com